

PAT-NO: JP362212480A
DOCUMENT-IDENTIFIER: JP 62212480 A
TITLE: FILLER FOR WATER-BASED COATING
PUBN-DATE: September 18, 1987

INVENTOR-INFORMATION:

| NAME | COUNTRY |
|--------------------|---------|
| MOTOYOSHI, SHIRO | |
| SAITO, TADASHI | |
| AZUMA, TOSHIO | |
| EBISUYA, NORITSUGU | |

ASSIGNEE-INFORMATION:

| NAME | COUNTRY |
|------------------|---------|
| MARUO CALCIUM KK | N/A |

APPL-NO: JP61057661
APPL-DATE: March 14, 1986

INT-CL (IPC): C09D007/12 , C09D005/02 , C08K009/04 , C08K009/04

ABSTRACT:

PURPOSE: To obtain an extender pigment which has excellent dispersibility in a water-based coating and gives a coating film with high gloss, by wet-milling an aqueous suspension of calcium carbonate on which a polycarboxylic acid dispersing agent of a specified composition has been adsorbed, in a manner to satisfy specified conditions.

CONSTITUTION: A precipitated calcium carbonate having an average particle diameter of $0.01 \sim 0.5\mu\text{m}$ is allowed to adsorb a sodium salt, an ammonium salt and/or an amino salt of a polymer of at least one α,β -unsaturated monocarboxylic acid (I) selected from among acrylic acid, methacrylic acid and crotonic acid and/or a copolymer of (I) with at least one α,β -unsaturated dicarboxylic acid (II) selected from maleic acid and itaconic acid. This calcium carbonate is allowed to stay in a continuous wet disperser for at least 0.5min to be wet-milled so that the value S calculated by the equation from the particle size distribution determined with an apparatus by photo extinction method of the centrifugal sedimentation analysis may satisfy the equation. The wet-milled calcium carbonate is then dried to form a powder.

COPYRIGHT: (C)1987,JPO&Japio